

SVEMA FOTO 200

BLACK & WHITE NEGATIVE FILM

FILM TYPE
Panchromatic
negative film

SPECTRAL SENSITIVITY
Panchromatic up to 750 nm.
Use an R72 infrared filter
for infrared effects.

BASE
Clear polyester base

BASE THICKNESS
0.10 mm (.004")

STABILITY
Excellent dimensional
stability

PACKAGING
Original factory packaging,
fresh

ORIGIN
Made in Ukraine



Photos by Christopher May

FINE GRAIN
Low grain,
low noise

HIGH RESOLUTION
Excellent detail
and sharpness

INFRARED CAPABLE
Expanded sensitivity
to near IR

STABLE BASE
Thin polyester base
for dimensional
stability

DEVELOPMENT GUIDE (Starting Points)

DEVELOPER	DILUTION	ISO	TIME (min)	TEMP.
D-76	Stock	200	8.5	20°C
Eco Pro	Stock	200	10	21°C
Eco Pro	1+1	200	12	20°C
HC-110	Dil J	200	60	20°C
Ilfosol 3	1+14	200	12	20°C
Ilfotec DD-X	1+4	200	8	20°C
Microphen	Stock	400	10	20°C

DEVELOPER	DILUTION	ISO	TIME (min)	TEMP.
Rodinal	1+25	200	7	20°C
Rodinal	1+50	200	14	20°C
TMax Dev	1+4	200	7.5	20°C
XT-3	Stock	200	10	21°C
XT-3	1+1	200	12	20°C
Xtol	Stock	200	10	21°C
Xtol	1+1	200	12	20°C